Old Orange-Δ10

Lab 5a-Color Wheel

Old Orange

Original
062822-1

Neph Sy	37.51
Whiting	18.67
EPK	9.55
Flint	34.26
Light Rutile	11.11
Water	60

Oxidation

1-3 Second Dip



2-3 Second Dips

Reduction

UMF

SiO_2:Al_2O_3 Ratio 8.81 :1		Alkali Metals 0.29		Alkaline Earths 0.71	
SiO_2 3.77	Collective "Al_2O_3" 0.43	Na_2O 0.23	K_2O 0.07	MgO 0.00	CaO 0.69
B_2O_3	Al_2O_3 0.43	Li_2O	CuO	SrO	BaO
TiO_2 0.00	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.01
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



EUMF

SiO_2:Al_2O_3 Ratio 4.13 :1		Alkali Metals 0.29		Alkaline Earths 0.71	
SiO_2 3.77	Collective "Al_2O_3" 0.91	Na_2O 0.23	K_2O 0.07	MgO 0.00	CaO 0.69
B_2O_3	Al_2O_3 0.43	Li_2O	CuO	SrO	BaO
TiO_2 0.49	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.01
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO

Ceramic Materials Workshop

ceramicmaterialsworkshop.com

Chrome Oxide (+11.11% Light Rutile)

Ceramic
Materials
Workshop

Old Orange 062822

ceramicmaterialsworkshop.com

Chrome Oxide (+11.11% Light Rutile)

0.5%

SiO_2:Al_2O_3 Ratio 4.13 :1		Alkali Metals 0.29		Alkaline Earths 0.71	
SiO_2 3.77	Collective "Al_2O_3" 0.91	Na_2O 0.23	K_2O 0.07	MgO 0.00	CaO 0.69
B_2O_3	Al_2O_3 0.43	Li_2O	CuO	SrO	BaO
TiO_2 0.49	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.01
Cr_2O_3 0.01	ZrO_2	P_2O_5		MnO_2	CoO



2%

SiO_2:Al_2O_3 Ratio 4.13 :1		Alkali Metals 0.29		Alkaline Earths 0.71	
SiO_2 3.77	Collective "Al_2O_3" 0.91	Na_2O 0.23	K_2O 0.07	MgO 0.00	CaO 0.69
B_2O_3	Al_2O_3 0.43	Li_2O	CuO	SrO	BaO
TiO_2 0.49	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.01
Cr_2O_3 0.05	ZrO_2	P_2O_5		MnO_2	CoO



Cobalt Carbonate (+11.11% Light Rutile)



Ceramic
Materials
Workshop

Old Orange 062822

ceramicmaterialsworkshop.com

Cobalt Carbonate (+11.11% Light Rutile)

0.5%

SiO_2:Al_2O_3 Ratio 4.13 :1		Alkali Metals 0.29		Alkaline Earths 0.71	
SiO_2 3.71	Collective "Al_2O_3" 0.90	Na_2O 0.22	K_2O 0.06	MgO 0.00	CaO 0.68
B_2O_3	Al_2O_3 0.42	Li_2O	CuO	SrO	BaO
TiO_2 0.48	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.01
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO 0.02



2%

SiO_2:Al_2O_3 Ratio 4.13 :1		Alkali Metals 0.28		Alkaline Earths 0.72	
SiO_2 3.55	Collective "Al_2O_3" 0.86	Na_2O 0.21	K_2O 0.06	MgO 0.00	CaO 0.65
B_2O_3	Al_2O_3 0.40	Li_2O	CuO	SrO	BaO
TiO_2 0.46	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.01
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO 0.06



Cobalt Oxide (+11.11% Light Rutile)



Ceramic
Materials
Workshop

Old Orange 062822

ceramicmaterialsworkshop.com

Cobalt Oxide (+11.11% Light Rutile)

0.5%

SiO_2:Al_2O_3 Ratio 4.13 :1		Alkali Metals 0.29		Alkaline Earths 0.71	
SiO_2 3.68	Collective "Al_2O_3" 0.89	Na_2O 0.22	K_2O 0.06	MgO 0.00	CaO 0.68
B_2O_3	Al_2O_3 0.42	Li_2O	CuO	SrO	BaO
TiO_2 0.47	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.01
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO 0.02



2%

SiO_2:Al_2O_3 Ratio 4.13 :1		Alkali Metals 0.27		Alkaline Earths 0.73	
SiO_2 3.43	Collective "Al_2O_3" 0.83	Na_2O 0.21	K_2O 0.06	MgO 0.00	CaO 0.63
B_2O_3	Al_2O_3 0.39	Li_2O	CuO	SrO	BaO
TiO_2 0.44	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.01
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO 0.09



Copper Carbonate (+11.11% Light Rutile)



Ceramic
Materials
Workshop

Old Orange 062822

ceramicmaterialsworkshop.com

Copper Carbonate (+11.11% Light Rutile)

1%

SiO_2:Al_2O_3 Ratio 4.13 :1		Alkali Metals 0.31		Alkaline Earths 0.69	
SiO_2 3.66	Collective "Al_2O_3" 0.89	Na_2O 0.22	K_2O 0.06	MgO 0.00	CaO 0.67
B_2O_3	Al_2O_3 0.41	Li_2O	CuO 0.03	SrO	BaO
TiO_2 0.47	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.01
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



4%

SiO_2:Al_2O_3 Ratio 4.13 :1		Alkali Metals 0.37		Alkaline Earths 0.63	
SiO_2 3.37	Collective "Al_2O_3" 0.82	Na_2O 0.20	K_2O 0.06	MgO 0.00	CaO 0.62
B_2O_3	Al_2O_3 0.38	Li_2O	CuO 0.11	SrO	BaO
TiO_2 0.43	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.01
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



Copper Oxide-Black (+11.11% Light Rutile)

Oxidation

Reduction

1%

1-3 Second Dip

2-3 Second Dips

1-3 Second Dip

2-3 Second Dips

4%

Ceramic
Materials
Workshop

Old Orange 062822

ceramicmaterialsworkshop.com

Copper Oxide-Black (+11.11% Light Rutile)

1%

SiO_2:Al_2O_3 Ratio 4.13 :1		Alkali Metals 0.33		Alkaline Earths 0.67	
SiO_2 3.60	Collective "Al_2O_3" 0.87	Na_2O 0.22	K_2O 0.06	MgO 0.00	CaO 0.66
B_2O_3	Al_2O_3 0.41	Li_2O	CuO 0.04	SrO	BaO
TiO_2 0.46	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.01
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



4%

SiO_2:Al_2O_3 Ratio 4.13 :1		Alkali Metals 0.40		Alkaline Earths 0.60	
SiO_2 3.18	Collective "Al_2O_3" 0.77	Na_2O 0.19	K_2O 0.06	MgO 0.00	CaO 0.59
B_2O_3	Al_2O_3 0.36	Li_2O	CuO 0.16	SrO	BaO
TiO_2 0.41	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.01
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



Red Iron Oxide (+11.11% Light Rutile)

Oxidation

Reduction

3%

1-3 Second Dip

2-3 Second Dips



1-3 Second Dip

2-3 Second Dips

9%

Ceramic
Materials
Workshop

Old Orange 062822

ceramicmaterialsworkshop.com

Red Iron Oxide (+11.11% Light Rutile)

3%

SiO_2:Al_2O_3 Ratio 4.13 :1		Alkali Metals 0.24		Alkaline Earths 0.76	
SiO_2 3.09	Collective "Al_2O_3" 0.75	Na_2O 0.19	K_2O 0.05	MgO 0.00	CaO 0.57
B_2O_3	Al_2O_3 0.35	Li_2O	CuO	SrO	BaO
TiO_2 0.40	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.19
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



9%

SiO_2:Al_2O_3 Ratio 4.13 :1		Alkali Metals 0.18		Alkaline Earths 0.82	
SiO_2 2.27	Collective "Al_2O_3" 0.55	Na_2O 0.14	K_2O 0.04	MgO 0.00	CaO 0.42
B_2O_3	Al_2O_3 0.26	Li_2O	CuO	SrO	BaO
TiO_2 0.29	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.40
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



Black Iron Oxide (+11.11% Light Rutile)

Oxidation

Reduction

3%

1-3 Second Dip

2-3 Second Dips

1-3 Second Dip

2-3 Second Dips

9%



Ceramic
Materials
Workshop

Old Orange 062822

ceramicmaterialsworkshop.com

Black Iron Oxide (+11.11% Light Rutile)

3%

SiO_2:Al_2O_3 Ratio 4.13 :1		Alkali Metals 0.22		Alkaline Earths 0.78	
SiO_2 2.83	Collective "Al_2O_3" 0.69	Na_2O 0.17	K_2O 0.05	MgO 0.00	CaO 0.52
B_2O_3	Al_2O_3 0.32	Li_2O	CuO	SrO	BaO
TiO_2 0.37	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.26
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



9%

SiO_2:Al_2O_3 Ratio 4.13 :1		Alkali Metals 0.15		Alkaline Earths 0.85	
SiO_2 1.89	Collective "Al_2O_3" 0.46	Na_2O 0.11	K_2O 0.03	MgO 0.00	CaO 0.35
B_2O_3	Al_2O_3 0.21	Li_2O	CuO	SrO	BaO
TiO_2 0.24	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.50
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



Yellow Iron Oxide (+11.11% Light Rutile)

Ceramic
Materials
Workshop

Old Orange 062822

Yellow Iron Oxide (+11.11% Light Rutile)

3%

SiO_2:Al_2O_3 Ratio 4.13 :1		Alkali Metals 0.25		Alkaline Earths 0.75	
SiO_2 3.16	Collective "Al_2O_3" 0.76	Na_2O 0.19	K_2O 0.06	MgO 0.00	CaO 0.58
B_2O_3	Al_2O_3 0.36	Li_2O	CuO	SrO	BaO
TiO_2 0.41	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.17
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



9%

SiO_2:Al_2O_3 Ratio 4.13 :1		Alkali Metals 0.19		Alkaline Earths 0.81	
SiO_2 2.38	Collective "Al_2O_3" 0.58	Na_2O 0.14	K_2O 0.04	MgO 0.00	CaO 0.44
B_2O_3	Al_2O_3 0.27	Li_2O	CuO	SrO	BaO
TiO_2 0.31	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.37
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



Manganese Dioxide (+11.11% Light Rutile)



Ceramic
Materials
Workshop

Old Orange 062822

ceramicmaterialsworkshop.com

Manganese Dioxide (+11.11% Light Rutile)

1%

SiO_2:Al_2O_3 Ratio 4.13 :1		Alkali Metals 0.28		Alkaline Earths 0.72	
SiO_2 3.62	Collective "Al_2O_3" 0.88	Na_2O 0.22	K_2O 0.06	MgO 0.00	CaO 0.66
B_2O_3	Al_2O_3 0.41	Li_2O	CuO	SrO	BaO
TiO_2 0.47	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.01
Cr_2O_3	ZrO_2	P_2O_5		MnO_2 0.04	CoO



4%

SiO_2:Al_2O_3 Ratio 4.13 :1		Alkali Metals 0.25		Alkaline Earths 0.75	
SiO_2 3.23	Collective "Al_2O_3" 0.78	Na_2O 0.20	K_2O 0.06	MgO 0.00	CaO 0.59
B_2O_3	Al_2O_3 0.37	Li_2O	CuO	SrO	BaO
TiO_2 0.42	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.01
Cr_2O_3	ZrO_2	P_2O_5		MnO_2 0.14	CoO



Vanadium Pentoxide (+11.11% Light Rutile)

Ceramic
Materials
Workshop

Old Orange 062822

ceramicmaterialsworkshop.com

Vanadium Pentoxide (+11.11% Light Rutile)

3%

SiO_2:Al_2O_3 Ratio 4.13 :1		Alkali Metals 0.29		Alkaline Earths 0.71	
SiO_2 3.77	Collective "Al_2O_3" 0.91	Na_2O 0.23	K_2O 0.07	MgO 0.00	CaO 0.69
B_2O_3	Al_2O_3 0.43	Li_2O	CuO	SrO	BaO
TiO_2 0.49	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.01
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



9%

SiO_2:Al_2O_3 Ratio 4.13 :1		Alkali Metals 0.29		Alkaline Earths 0.71	
SiO_2 3.77	Collective "Al_2O_3" 0.91	Na_2O 0.23	K_2O 0.07	MgO 0.00	CaO 0.69
B_2O_3	Al_2O_3 0.43	Li_2O	CuO	SrO	BaO
TiO_2 0.49	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.01
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



Dark Rutile (+11.11% Light Rutile)



Ceramic
Materials
Workshop

Old Orange 062822

ceramicmaterialsworkshop.com

Dark Rutile (+11.11% Light Rutile)

3%

SiO_2:Al_2O_3 Ratio 3.64 :1		Alkali Metals 0.29		Alkaline Earths 0.71	
SiO_2 3.72	Collective "Al_2O_3" 1.02	Na_2O 0.23	K_2O 0.06	MgO 0.00	CaO 0.68
B_2O_3	Al_2O_3 0.42	Li_2O	CuO	SrO	BaO
TiO_2 0.60	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.02
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



9%

SiO_2:Al_2O_3 Ratio 2.94 :1		Alkali Metals 0.28		Alkaline Earths 0.72	
SiO_2 3.62	Collective "Al_2O_3" 1.23	Na_2O 0.22	K_2O 0.06	MgO 0.00	CaO 0.67
B_2O_3	Al_2O_3 0.41	Li_2O	CuO	SrO	BaO
TiO_2 0.82	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.05
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



Light Rutile (+11.11% Light Rutile)



Ceramic
Materials
Workshop

Old Orange 062822

ceramicmaterialsworkshop.com

Light Rutile (+11.11% Light Rutile)

3%

SiO_2:Al_2O_3 Ratio 3.61 :1		Alkali Metals 0.29		Alkaline Earths 0.71	
SiO_2 3.77	Collective "Al_2O_3" 1.04	Na_2O 0.23	K_2O 0.07	MgO 0.00	CaO 0.69
B_2O_3	Al_2O_3 0.43	Li_2O	CuO	SrO	BaO
TiO_2 0.62	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.01
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



9%

SiO_2:Al_2O_3 Ratio 2.89 :1		Alkali Metals 0.29		Alkaline Earths 0.71	
SiO_2 3.77	Collective "Al_2O_3" 1.30	Na_2O 0.23	K_2O 0.07	MgO 0.00	CaO 0.69
B_2O_3	Al_2O_3 0.43	Li_2O	CuO	SrO	BaO
TiO_2 0.88	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.01
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



Titanium Dioxide (+11.11% Light Rutile)



Ceramic
Materials
Workshop

Old Orange 062822

ceramicmaterialsworkshop.com

Titanium Dioxide (+11.11% Light Rutile)

3%

SiO_2:Al_2O_3 Ratio 3.59 :1		Alkali Metals 0.29		Alkaline Earths 0.71	
SiO_2 3.77	Collective "Al_2O_3" 1.05	Na_2O 0.23	K_2O 0.07	MgO 0.00	CaO 0.69
B_2O_3	Al_2O_3 0.43	Li_2O	CuO	SrO	BaO
TiO_2 0.62	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.01
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



9%

SiO_2:Al_2O_3 Ratio 2.85 :1		Alkali Metals 0.29		Alkaline Earths 0.71	
SiO_2 3.77	Collective "Al_2O_3" 1.32	Na_2O 0.23	K_2O 0.07	MgO 0.00	CaO 0.69
B_2O_3	Al_2O_3 0.43	Li_2O	CuO	SrO	BaO
TiO_2 0.89	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.01
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



Nickel Carbonate (+11.11% Light Rutile)

Oxidation

Reduction

2%

1-3 Second Dip



2-3 Second Dips

1-3 Second Dip

2-3 Second Dips

6%

Ceramic
Materials
Workshop

Old Orange 062822

ceramicmaterialsworkshop.com

Nickel Carbonate (+11.11% Light Rutile)

2%

SiO_2:Al_2O_3 Ratio 3.87 :1		Alkali Metals 0.29		Alkaline Earths 0.71	
SiO_2 3.77	Collective "Al_2O_3" 0.97	Na_2O 0.23	K_2O 0.07	MgO 0.00	CaO 0.69
B_2O_3	Al_2O_3 0.43	Li_2O	CuO	SrO	BaO
TiO_2 0.49	NiO 0.06	Bi_2O_3	SnO_2	ZnO	FeO 0.01
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



6%

SiO_2:Al_2O_3 Ratio 3.43 :1		Alkali Metals 0.29		Alkaline Earths 0.71	
SiO_2 3.77	Collective "Al_2O_3" 1.10	Na_2O 0.23	K_2O 0.07	MgO 0.00	CaO 0.69
B_2O_3	Al_2O_3 0.43	Li_2O	CuO	SrO	BaO
TiO_2 0.49	NiO 0.19	Bi_2O_3	SnO_2	ZnO	FeO 0.01
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



Nickel Oxide-Black (+11.11% Light Rutile)

Oxidation

Reduction

2%

1-3 Second Dip

2-3 Second Dips

1-3 Second Dip

2-3 Second Dips

6%

Ceramic
Materials
Workshop

Old Orange 062822

ceramicmaterialsworkshop.com

Nickel Oxide-Black (+11.11% Light Rutile)

2%

SiO_2:Al_2O_3 Ratio 3.76 :1		Alkali Metals 0.29		Alkaline Earths 0.71	
SiO_2 3.77	Collective "Al_2O_3" 1.00	Na_2O 0.23	K_2O 0.07	MgO 0.00	CaO 0.69
B_2O_3	Al_2O_3 0.43	Li_2O	CuO	SrO	BaO
TiO_2 0.49	NiO 0.09	Bi_2O_3	SnO_2	ZnO	FeO 0.01
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



6%

SiO_2:Al_2O_3 Ratio 3.20 :1		Alkali Metals 0.29		Alkaline Earths 0.71	
SiO_2 3.77	Collective "Al_2O_3" 1.18	Na_2O 0.23	K_2O 0.07	MgO 0.00	CaO 0.69
B_2O_3	Al_2O_3 0.43	Li_2O	CuO	SrO	BaO
TiO_2 0.49	NiO 0.26	Bi_2O_3	SnO_2	ZnO	FeO 0.01
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



Tin Oxide (+11.11% Light Rutile)



Ceramic
Materials
Workshop

Old Orange 062822

ceramicmaterialsworkshop.com

Tin Oxide (+11.11% Light Rutile)

3%

SiO_2:Al_2O_3 Ratio 4.13 :1		Alkali Metals 0.34		Alkaline Earths 0.66	
SiO_2 3.51	Collective "Al_2O_3" 0.85	Na_2O 0.21	K_2O 0.06	MgO 0.00	CaO 0.65
B_2O_3	Al_2O_3 0.40	Li_2O	CuO	SrO	BaO
TiO_2 0.45	NiO	Bi_2O_3	SnO_2 0.07	ZnO	FeO 0.01
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



6%

SiO_2:Al_2O_3 Ratio 4.13 :1		Alkali Metals 0.38		Alkaline Earths 0.62	
SiO_2 3.29	Collective "Al_2O_3" 0.80	Na_2O 0.20	K_2O 0.06	MgO 0.00	CaO 0.60
B_2O_3	Al_2O_3 0.37	Li_2O	CuO	SrO	BaO
TiO_2 0.42	NiO	Bi_2O_3	SnO_2 0.13	ZnO	FeO 0.01
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



Zirconium Silicate (+11.11% Light Rutile)

Oxidation

Reduction

5%

1-3 Second Dip

2-3 Second Dips



1-3 Second Dip

2-3 Second Dips

10%

Ceramic
Materials
Workshop

Old Orange 062822

ceramicmaterialsworkshop.com

Zirconium Silicate (+11.11% Light Rutile)

5%

SiO_2:Al_2O_3 Ratio 4.24 :1		Alkali Metals 0.29		Alkaline Earths 0.71	
SiO_2 3.87	Collective "Al_2O_3" 0.91	Na_2O 0.23	K_2O 0.07	MgO 0.00	CaO 0.69
B_2O_3	Al_2O_3 0.43	Li_2O	CuO	SrO	BaO
TiO_2 0.49	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.01
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



10%

SiO_2:Al_2O_3 Ratio 4.35 :1		Alkali Metals 0.29		Alkaline Earths 0.71	
SiO_2 3.97	Collective "Al_2O_3" 0.91	Na_2O 0.23	K_2O 0.07	MgO 0.00	CaO 0.69
B_2O_3	Al_2O_3 0.43	Li_2O	CuO	SrO	BaO
TiO_2 0.49	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.01
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



Stain Dark Red 6021 (+11.11% Light Rutile)

Oxidation

Reduction

5%

1-3 Second Dip

2-3 Second Dips

1-3 Second Dip

2-3 Second Dips

10%

Ceramic
Materials
Workshop

Old Orange 062822

ceramicmaterialsworkshop.com

Stain Dark Red 6021(+11.11% Light Rutile)

5%

SiO_2:Al_2O_3 Ratio 4.13 :1		Alkali Metals 0.29		Alkaline Earths 0.71	
SiO_2 3.77	Collective "Al_2O_3" 0.91	Na_2O 0.23	K_2O 0.07	MgO 0.00	CaO 0.69
B_2O_3	Al_2O_3 0.43	Li_2O	CuO	SrO	BaO
TiO_2 0.49	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.01
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



10%

SiO_2:Al_2O_3 Ratio 4.13 :1		Alkali Metals 0.29		Alkaline Earths 0.71	
SiO_2 3.77	Collective "Al_2O_3" 0.91	Na_2O 0.23	K_2O 0.07	MgO 0.00	CaO 0.69
B_2O_3	Al_2O_3 0.43	Li_2O	CuO	SrO	BaO
TiO_2 0.49	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.01
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



Silicon Carbide-30 Mesh (+11.11% Light Rutile)

Oxidation

Reduction

3%

1-3 Second Dip

2-3 Second Dips

1-3 Second Dip

2-3 Second Dips

9%

Ceramic
Materials
Workshop

Old Orange 062822

ceramicmaterialsworkshop.com

Silicon Carbide-30 Mesh (+11.11% Light Rutile)

3%

SiO_2:Al_2O_3 Ratio 4.27 :1		Alkali Metals 0.29		Alkaline Earths 0.71	
SiO_2 3.90	Collective "Al_2O_3" 0.91	Na_2O 0.23	K_2O 0.07	MgO 0.00	CaO 0.69
B_2O_3	Al_2O_3 0.43	Li_2O	CuO	SrO	BaO
TiO_2 0.49	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.01
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



9%

SiO_2:Al_2O_3 Ratio 4.55 :1		Alkali Metals 0.29		Alkaline Earths 0.71	
SiO_2 4.15	Collective "Al_2O_3" 0.91	Na_2O 0.23	K_2O 0.07	MgO 0.00	CaO 0.69
B_2O_3	Al_2O_3 0.43	Li_2O	CuO	SrO	BaO
TiO_2 0.49	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.01
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



Silicon Carbide-800 Mesh (+11.11% Light Rutile)



Ceramic
Materials
Workshop

Old Orange 062822

ceramicmaterialsworkshop.com

Silicon Carbide-800 Mesh (+11.11% Light Rutile)

3%

SiO_2:Al_2O_3 Ratio 4.27 :1		Alkali Metals 0.29		Alkaline Earths 0.71	
SiO_2 3.90	Collective "Al_2O_3" 0.91	Na_2O 0.23	K_2O 0.07	MgO 0.00	CaO 0.69
B_2O_3	Al_2O_3 0.43	Li_2O	CuO	SrO	BaO
TiO_2 0.49	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.01
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



9%

SiO_2:Al_2O_3 Ratio 4.55 :1		Alkali Metals 0.29		Alkaline Earths 0.71	
SiO_2 4.15	Collective "Al_2O_3" 0.91	Na_2O 0.23	K_2O 0.07	MgO 0.00	CaO 0.69
B_2O_3	Al_2O_3 0.43	Li_2O	CuO	SrO	BaO
TiO_2 0.49	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.01
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO