Peacock-Δ10

Lab 5a-Color Wheel

Peacock

Original
062922-1

Neph Sy	36.62
Barium Carb	46.57
EPK	6.63
Flint	10.19
Copper Carbonate	3.09
Water	60

Oxidation

1-3 Second Dip



2-3 Second Dips

Reduction



UMF

$SiO_2:Al_2O_3$ Ratio 5.80 :1		Alkali Metals 0.25		Alkaline Earths 0.75	
SiO_2 1.88	Collective "Al_2O_3" 0.32	Na_2O 0.19	K_2O 0.05	MgO 0.00	CaO 0.01
B_2O_3	Al_2O_3 0.32	Li_2O	CuO	SrO	BaO 0.74
TiO_2 0.00	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.00
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



EUMF

$SiO_2:Al_2O_3$ Ratio 5.80 :1		Alkali Metals 0.30		Alkaline Earths 0.70	
SiO_2 1.74	Collective "Al_2O_3" 0.30	Na_2O 0.18	K_2O 0.05	MgO 0.00	CaO 0.01
B_2O_3	Al_2O_3 0.30	Li_2O	CuO 0.07	SrO	BaO 0.69
TiO_2 0.00	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.00
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO

Ceramic Materials Workshop

ceramicmaterialsworkshop.com

Chrome Oxide



Ceramic
Materials
Workshop

Peacock 062922

ceramicmaterialsworkshop.com

Chrome Oxide

0.5%

SiO_2:Al_2O_3 Ratio 5.80 :1		Alkali Metals 0.30		Alkaline Earths 0.70	
SiO_2 1.74	Collective "Al_2O_3" 0.30	Na_2O 0.18	K_2O 0.05	MgO 0.00	CaO 0.01
B_2O_3	Al_2O_3 0.30	Li_2O	CuO 0.07	SrO	BaO 0.69
TiO_2 0.00	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.00
Cr_2O_3 0.01	ZrO_2	P_2O_5		MnO_2	CoO



2%

SiO_2:Al_2O_3 Ratio 5.80 :1		Alkali Metals 0.30		Alkaline Earths 0.70	
SiO_2 1.74	Collective "Al_2O_3" 0.30	Na_2O 0.18	K_2O 0.05	MgO 0.00	CaO 0.01
B_2O_3	Al_2O_3 0.30	Li_2O	CuO 0.07	SrO	BaO 0.69
TiO_2 0.00	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.00
Cr_2O_3 0.04	ZrO_2	P_2O_5		MnO_2	CoO



Cobalt Carbonate



Ceramic
Materials
Workshop

Peacock 062922

ceramicmaterialsworkshop.com

Cobalt Carbonate

0.5%

SiO_2:Al_2O_3 Ratio 5.80 :1		Alkali Metals 0.30		Alkaline Earths 0.70	
SiO_2 1.72	Collective "Al_2O_3" 0.30	Na_2O 0.17	K_2O 0.05	MgO 0.00	CaO 0.01
B_2O_3	Al_2O_3 0.30	Li_2O	CuO 0.07	SrO	BaO 0.68
TiO_2 0.00	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.00
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO 0.01



2%

SiO_2:Al_2O_3 Ratio 5.80 :1		Alkali Metals 0.29		Alkaline Earths 0.71	
SiO_2 1.66	Collective "Al_2O_3" 0.29	Na_2O 0.17	K_2O 0.05	MgO 0.00	CaO 0.01
B_2O_3	Al_2O_3 0.29	Li_2O	CuO 0.07	SrO	BaO 0.65
TiO_2 0.00	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.00
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO 0.05



Cobalt Oxide



Ceramic
Materials
Workshop

Peacock 062922

ceramicmaterialsworkshop.com

Cobalt Oxide

0.5%

SiO_2:Al_2O_3 Ratio 5.80 :1		Alkali Metals 0.29		Alkaline Earths 0.71	
SiO_2 1.71	Collective "Al_2O_3" 0.29	Na_2O 0.17	K_2O 0.05	MgO 0.00	CaO 0.01
B_2O_3	Al_2O_3 0.29	Li_2O	CuO 0.07	SrO	BaO 0.67
TiO_2 0.00	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.00
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO 0.02



2%

SiO_2:Al_2O_3 Ratio 5.80 :1		Alkali Metals 0.28		Alkaline Earths 0.72	
SiO_2 1.62	Collective "Al_2O_3" 0.28	Na_2O 0.16	K_2O 0.05	MgO 0.00	CaO 0.01
B_2O_3	Al_2O_3 0.28	Li_2O	CuO 0.07	SrO	BaO 0.64
TiO_2 0.00	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.00
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO 0.07



Copper Carbonate



Ceramic
Materials
Workshop

Peacock 062922

ceramicmaterialsworkshop.com

Copper Carbonate

1%

SiO_2:Al_2O_3 Ratio 5.80 :1		Alkali Metals 0.32		Alkaline Earths 0.68	
SiO_2 1.70	Collective "Al_2O_3" 0.29	Na_2O 0.17	K_2O 0.05	MgO 0.00	CaO 0.01
B_2O_3	Al_2O_3 0.29	Li_2O	CuO 0.09	SrO	BaO 0.67
TiO_2 0.00	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.00
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



4%

SiO_2:Al_2O_3 Ratio 5.80 :1		Alkali Metals 0.36		Alkaline Earths 0.64	
SiO_2 1.59	Collective "Al_2O_3" 0.27	Na_2O 0.16	K_2O 0.05	MgO 0.00	CaO 0.01
B_2O_3	Al_2O_3 0.27	Li_2O	CuO 0.15	SrO	BaO 0.63
TiO_2 0.00	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.00
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



Copper Oxide-Black



Ceramic
Materials
Workshop

Peacock 062922

ceramicmaterialsworkshop.com

Copper Oxide-Black

1%

SiO_2:Al_2O_3 Ratio 5.80 :1		Alkali Metals 0.33		Alkaline Earths 0.67	
SiO_2 1.68	Collective "Al_2O_3" 0.29	Na_2O 0.17	K_2O 0.05	MgO 0.00	CaO 0.01
B_2O_3	Al_2O_3 0.29	Li_2O	CuO 0.11	SrO	BaO 0.66
TiO_2 0.00	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.00
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



4%

SiO_2:Al_2O_3 Ratio 5.80 :1		Alkali Metals 0.39		Alkaline Earths 0.61	
SiO_2 1.52	Collective "Al_2O_3" 0.26	Na_2O 0.15	K_2O 0.04	MgO 0.00	CaO 0.01
B_2O_3	Al_2O_3 0.26	Li_2O	CuO 0.19	SrO	BaO 0.60
TiO_2 0.00	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.00
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



Red Iron Oxide

Ceramic
Materials
Workshop

Peacock 062922

ceramicmaterialsworkshop.com

Red Iron Oxide

3%

SiO_2:Al_2O_3 Ratio 5.80 :1		Alkali Metals 0.26		Alkaline Earths 0.74	
SiO_2 1.48	Collective "Al_2O_3" 0.26	Na_2O 0.15	K_2O 0.04	MgO 0.00	CaO 0.01
B_2O_3	Al_2O_3 0.25	Li_2O	CuO 0.06	SrO	BaO 0.58
TiO_2 0.00	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.15
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



9%

SiO_2:Al_2O_3 Ratio 5.80 :1		Alkali Metals 0.20		Alkaline Earths 0.80	
SiO_2 1.14	Collective "Al_2O_3" 0.20	Na_2O 0.12	K_2O 0.03	MgO 0.00	CaO 0.00
B_2O_3	Al_2O_3 0.20	Li_2O	CuO 0.05	SrO	BaO 0.45
TiO_2 0.00	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.35
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



Black Iron Oxide

Ceramic
Materials
Workshop

Peacock 062922

ceramicmaterialsworkshop.com

Black Iron Oxide

3%

SiO_2:Al_2O_3 Ratio 5.80 :1		Alkali Metals 0.24		Alkaline Earths 0.76	
SiO_2 1.38	Collective "Al_2O_3" 0.24	Na_2O 0.14	K_2O 0.04	MgO 0.00	CaO 0.01
B_2O_3	Al_2O_3 0.24	Li_2O	CuO 0.06	SrO	BaO 0.54
TiO_2 0.00	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.21
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



9%

SiO_2:Al_2O_3 Ratio 5.80 :1		Alkali Metals 0.17		Alkaline Earths 0.83	
SiO_2 0.98	Collective "Al_2O_3" 0.17	Na_2O 0.10	K_2O 0.03	MgO 0.00	CaO 0.00
B_2O_3	Al_2O_3 0.17	Li_2O	CuO 0.04	SrO	BaO 0.38
TiO_2 0.00	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.44
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



Yellow Iron Oxide

Oxidation

Reduction

3%

1-3 Second Dip

2-3 Second Dips

1-3 Second Dip

2-3 Second Dips

9%







Ceramic
Materials
Workshop

Peacock 062922

ceramicmaterialsworkshop.com

Yellow Iron Oxide

3%

SiO_2:Al_2O_3 Ratio 5.80 :1		Alkali Metals 0.26		Alkaline Earths 0.74	
SiO_2 1.51	Collective "Al_2O_3" 0.26	Na_2O 0.15	K_2O 0.04	MgO 0.00	CaO 0.01
B_2O_3	Al_2O_3 0.26	Li_2O	CuO 0.06	SrO	BaO 0.60
TiO_2 0.00	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.14
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



9%

SiO_2:Al_2O_3 Ratio 5.80 :1		Alkali Metals 0.21		Alkaline Earths 0.79	
SiO_2 1.19	Collective "Al_2O_3" 0.21	Na_2O 0.12	K_2O 0.03	MgO 0.00	CaO 0.00
B_2O_3	Al_2O_3 0.20	Li_2O	CuO 0.05	SrO	BaO 0.47
TiO_2 0.00	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.32
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



Manganese Dioxide

Oxidation

Reduction

1%

1-3 Second Dip



2-3 Second Dips

1-3 Second Dip

2-3 Second Dips

4%

Ceramic
Materials
Workshop

Peacock 062922

ceramicmaterialsworkshop.com

Manganese Dioxide

1%

SiO_2:Al_2O_3 Ratio 5.80 :1		Alkali Metals 0.29		Alkaline Earths 0.71	
SiO_2 1.69	Collective "Al_2O_3" 0.29	Na_2O 0.17	K_2O 0.05	MgO 0.00	CaO 0.01
B_2O_3	Al_2O_3 0.29	Li_2O	CuO 0.07	SrO	BaO 0.66
TiO_2 0.00	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.00
Cr_2O_3	ZrO_2	P_2O_5		MnO_2 0.03	CoO



4%

SiO_2:Al_2O_3 Ratio 5.80 :1		Alkali Metals 0.26		Alkaline Earths 0.74	
SiO_2 1.54	Collective "Al_2O_3" 0.26	Na_2O 0.16	K_2O 0.04	MgO 0.00	CaO 0.01
B_2O_3	Al_2O_3 0.26	Li_2O	CuO 0.06	SrO	BaO 0.61
TiO_2 0.00	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.00
Cr_2O_3	ZrO_2	P_2O_5		MnO_2 0.12	CoO



Vanadium Pentoxide



Ceramic
Materials
Workshop

Peacock 062922

ceramicmaterialsworkshop.com

Vanadium Pentoxide

3%

SiO_2:Al_2O_3 Ratio 5.80 :1		Alkali Metals 0.30		Alkaline Earths 0.70	
SiO_2 1.74	Collective "Al_2O_3" 0.30	Na_2O 0.18	K_2O 0.05	MgO 0.00	CaO 0.01
B_2O_3	Al_2O_3 0.30	Li_2O	CuO 0.07	SrO	BaO 0.69
TiO_2 0.00	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.00
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



9%

SiO_2:Al_2O_3 Ratio 5.80 :1		Alkali Metals 0.30		Alkaline Earths 0.70	
SiO_2 1.74	Collective "Al_2O_3" 0.30	Na_2O 0.18	K_2O 0.05	MgO 0.00	CaO 0.01
B_2O_3	Al_2O_3 0.30	Li_2O	CuO 0.07	SrO	BaO 0.69
TiO_2 0.00	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.00
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



Dark Rutile

Ceramic
Materials
Workshop

Peacock 062922

ceramicmaterialsworkshop.com

Dark Rutile

3%

SiO_2:Al_2O_3 Ratio 4.39 :1		Alkali Metals 0.30		Alkaline Earths 0.70	
SiO_2 1.73	Collective "Al_2O_3" 0.39	Na_2O 0.18	K_2O 0.05	MgO 0.00	CaO 0.01
B_2O_3	Al_2O_3 0.30	Li_2O	CuO 0.07	SrO	BaO 0.68
TiO_2 0.10	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.01
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



9%

SiO_2:Al_2O_3 Ratio 2.95 :1		Alkali Metals 0.29		Alkaline Earths 0.71	
SiO_2 1.69	Collective "Al_2O_3" 0.57	Na_2O 0.17	K_2O 0.05	MgO 0.00	CaO 0.01
B_2O_3	Al_2O_3 0.29	Li_2O	CuO 0.07	SrO	BaO 0.67
TiO_2 0.28	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.04
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



Light Rutile



Ceramic
Materials
Workshop

Peacock 062922

ceramicmaterialsworkshop.com

Light Rutile

3%

SiO_2:Al_2O_3 Ratio 4.31 :1		Alkali Metals 0.30		Alkaline Earths 0.70	
SiO_2 1.74	Collective "Al_2O_3" 0.40	Na_2O 0.18	K_2O 0.05	MgO 0.00	CaO 0.01
B_2O_3	Al_2O_3 0.30	Li_2O	CuO 0.07	SrO	BaO 0.69
TiO_2 0.10	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.00
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



9%

SiO_2:Al_2O_3 Ratio 2.85 :1		Alkali Metals 0.30		Alkaline Earths 0.70	
SiO_2 1.74	Collective "Al_2O_3" 0.61	Na_2O 0.18	K_2O 0.05	MgO 0.00	CaO 0.01
B_2O_3	Al_2O_3 0.30	Li_2O	CuO 0.07	SrO	BaO 0.69
TiO_2 0.31	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.01
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



Titanium Dioxide



Ceramic
Materials
Workshop

Peacock 062922

ceramicmaterialsworkshop.com

Titanium Dioxide

3%

$SiO_2:Al_2O_3$ Ratio 4.27 :1		Alkali Metals 0.30		Alkaline Earths 0.70	
SiO_2 1.74	Collective "Al_2O_3" 0.41	Na_2O 0.18	K_2O 0.05	MgO 0.00	CaO 0.01
B_2O_3	Al_2O_3 0.30	Li_2O	CuO 0.07	SrO	BaO 0.69
TiO_2 0.11	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.00
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



9%

$SiO_2:Al_2O_3$ Ratio 2.79 :1		Alkali Metals 0.30		Alkaline Earths 0.70	
SiO_2 1.74	Collective "Al_2O_3" 0.62	Na_2O 0.18	K_2O 0.05	MgO 0.00	CaO 0.01
B_2O_3	Al_2O_3 0.30	Li_2O	CuO 0.07	SrO	BaO 0.69
TiO_2 0.32	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.00
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



Nickel Carbonate

Oxidation

Reduction

2%

1-3 Second Dip

2-3 Second Dips

1-3 Second Dip

2-3 Second Dips

6%

Ceramic
Materials
Workshop

Peacock 062922

ceramicmaterialsworkshop.com

Nickel Carbonate

2%

SiO_2:Al_2O_3 Ratio 4.99 :1		Alkali Metals 0.30		Alkaline Earths 0.70	
SiO_2 1.74	Collective "Al_2O_3" 0.35	Na_2O 0.18	K_2O 0.05	MgO 0.00	CaO 0.01
B_2O_3	Al_2O_3 0.30	Li_2O	CuO 0.07	SrO	BaO 0.69
TiO_2 0.00	NiO 0.05	Bi_2O_3	SnO_2	ZnO	FeO 0.00
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



6%

SiO_2:Al_2O_3 Ratio 3.90 :1		Alkali Metals 0.30		Alkaline Earths 0.70	
SiO_2 1.74	Collective "Al_2O_3" 0.45	Na_2O 0.18	K_2O 0.05	MgO 0.00	CaO 0.01
B_2O_3	Al_2O_3 0.30	Li_2O	CuO 0.07	SrO	BaO 0.69
TiO_2 0.00	NiO 0.15	Bi_2O_3	SnO_2	ZnO	FeO 0.00
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



Nickel Oxide-Black

Ceramic
Materials
Workshop

Peacock 062922

ceramicmaterialsworkshop.com

Nickel Oxide-Black

2%

SiO_2:Al_2O_3 Ratio 4.71 :1		Alkali Metals 0.30		Alkaline Earths 0.70	
SiO_2 1.74	Collective "Al_2O_3" 0.37	Na_2O 0.18	K_2O 0.05	MgO 0.00	CaO 0.01
B_2O_3	Al_2O_3 0.30	Li_2O	CuO 0.07	SrO	BaO 0.69
TiO_2 0.00	NiO 0.07	Bi_2O_3	SnO_2	ZnO	FeO 0.00
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



6%

SiO_2:Al_2O_3 Ratio 3.41 :1		Alkali Metals 0.30		Alkaline Earths 0.70	
SiO_2 1.74	Collective "Al_2O_3" 0.51	Na_2O 0.18	K_2O 0.05	MgO 0.00	CaO 0.01
B_2O_3	Al_2O_3 0.30	Li_2O	CuO 0.07	SrO	BaO 0.69
TiO_2 0.00	NiO 0.21	Bi_2O_3	SnO_2	ZnO	FeO 0.00
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



Tin Oxide

Ceramic
Materials
Workshop

Peacock 062922

ceramicmaterialsworkshop.com

Tin Oxide

3%

SiO_2:Al_2O_3 Ratio 5.80 :1		Alkali Metals 0.34		Alkaline Earths 0.66	
SiO_2 1.65	Collective "Al_2O_3" 0.28	Na_2O 0.17	K_2O 0.05	MgO 0.00	CaO 0.01
B_2O_3	Al_2O_3 0.28	Li_2O	CuO 0.07	SrO	BaO 0.65
TiO_2 0.00	NiO	Bi_2O_3	SnO_2 0.05	ZnO	FeO 0.00
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



6%

SiO_2:Al_2O_3 Ratio 5.80 :1		Alkali Metals 0.37		Alkaline Earths 0.63	
SiO_2 1.56	Collective "Al_2O_3" 0.27	Na_2O 0.16	K_2O 0.05	MgO 0.00	CaO 0.01
B_2O_3	Al_2O_3 0.27	Li_2O	CuO 0.07	SrO	BaO 0.62
TiO_2 0.00	NiO	Bi_2O_3	SnO_2 0.10	ZnO	FeO 0.00
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



Zirconium Silicate



Ceramic
Materials
Workshop

Peacock 062922

ceramicmaterialsworkshop.com

Zirconium Silicate

5%

SiO_2:Al_2O_3 Ratio 6.07 :1		Alkali Metals 0.30		Alkaline Earths 0.70	
SiO_2 1.82	Collective "Al_2O_3" 0.30	Na_2O 0.18	K_2O 0.05	MgO 0.00	CaO 0.01
B_2O_3	Al_2O_3 0.30	Li_2O	CuO 0.07	SrO	BaO 0.69
TiO_2 0.00	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.00
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



10%

SiO_2:Al_2O_3 Ratio 6.33 :1		Alkali Metals 0.30		Alkaline Earths 0.70	
SiO_2 1.90	Collective "Al_2O_3" 0.30	Na_2O 0.18	K_2O 0.05	MgO 0.00	CaO 0.01
B_2O_3	Al_2O_3 0.30	Li_2O	CuO 0.07	SrO	BaO 0.69
TiO_2 0.00	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.00
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



Stain Dark Red 6021

Ceramic
Materials
Workshop

Peacock 062922

ceramicmaterialsworkshop.com

Stain Dark Red 6021

5%

SiO_2:Al_2O_3 Ratio 5.80 :1		Alkali Metals 0.30		Alkaline Earths 0.70	
SiO_2 1.74	Collective "Al_2O_3" 0.30	Na_2O 0.18	K_2O 0.05	MgO 0.00	CaO 0.01
B_2O_3	Al_2O_3 0.30	Li_2O	CuO 0.07	SrO	BaO 0.69
TiO_2 0.00	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.00
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



10%

SiO_2:Al_2O_3 Ratio 5.80 :1		Alkali Metals 0.30		Alkaline Earths 0.70	
SiO_2 1.74	Collective "Al_2O_3" 0.30	Na_2O 0.18	K_2O 0.05	MgO 0.00	CaO 0.01
B_2O_3	Al_2O_3 0.30	Li_2O	CuO 0.07	SrO	BaO 0.69
TiO_2 0.00	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.00
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



Silicon Carbide-30 Mesh

Oxidation

Reduction

3%

1-3 Second Dip

2-3 Second Dips

1-3 Second Dip

2-3 Second Dips

9%

Ceramic
Materials
Workshop

Peacock 062922

ceramicmaterialsworkshop.com

Silicon Carbide-30 Mesh

3%

SiO_2:Al_2O_3 Ratio 6.14 :1		Alkali Metals 0.30		Alkaline Earths 0.70	
SiO_2 1.85	Collective "Al_2O_3" 0.30	Na_2O 0.18	K_2O 0.05	MgO 0.00	CaO 0.01
B_2O_3	Al_2O_3 0.30	Li_2O	CuO 0.07	SrO	BaO 0.69
TiO_2 0.00	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.00
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



9%

SiO_2:Al_2O_3 Ratio 6.82 :1		Alkali Metals 0.30		Alkaline Earths 0.70	
SiO_2 2.05	Collective "Al_2O_3" 0.30	Na_2O 0.18	K_2O 0.05	MgO 0.00	CaO 0.01
B_2O_3	Al_2O_3 0.30	Li_2O	CuO 0.07	SrO	BaO 0.69
TiO_2 0.00	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.00
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



Silicon Carbide-800 Mesh



Ceramic
Materials
Workshop

Peacock 062922

ceramicmaterialsworkshop.com

Silicon Carbide-800 Mesh

3%

SiO_2:Al_2O_3 Ratio 6.14 :1		Alkali Metals 0.30		Alkaline Earths 0.70	
SiO_2 1.85	Collective "Al_2O_3" 0.30	Na_2O 0.18	K_2O 0.05	MgO 0.00	CaO 0.01
B_2O_3	Al_2O_3 0.30	Li_2O	CuO 0.07	SrO	BaO 0.69
TiO_2 0.00	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.00
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO



9%

SiO_2:Al_2O_3 Ratio 6.82 :1		Alkali Metals 0.30		Alkaline Earths 0.70	
SiO_2 2.05	Collective "Al_2O_3" 0.30	Na_2O 0.18	K_2O 0.05	MgO 0.00	CaO 0.01
B_2O_3	Al_2O_3 0.30	Li_2O	CuO 0.07	SrO	BaO 0.69
TiO_2 0.00	NiO	Bi_2O_3	SnO_2	ZnO	FeO 0.00
Cr_2O_3	ZrO_2	P_2O_5		MnO_2	CoO