


Purple Rain- Δ 10

Lab 5b-Color Wheel 2


Purple Rain

Original
062722-1

Neph Sy	40.93
Dolomite	30.27
EPK	5.04
Flint	23.76
Cobalt Carbonate	1
Water	60



1-3 Second Dip



2-3 Second Dips




Oxidation

Reduction

UMF

SiO ₂ :Al ₂ O ₃ Ratio 7.93 :1		Alkali Metals 0.21		Alkaline Earths 0.79	
SiO ₂ 2.03	Collective "Al ₂ O ₃ " 0.26	Na ₂ O 0.16	K ₂ O 0.05	MgO 0.39	CaO 0.40
B ₂ O ₃	Al ₂ O ₃ 0.26	Li ₂ O	CuO	SrO	BaO
TiO ₂ 0.00	NiO	Bi ₂ O ₃	SnO ₂	ZnO	FeO 0.00
Cr ₂ O ₃	ZrO ₂	P ₂ O ₅		MnO ₂	CoO




EUMF

SiO ₂ :Al ₂ O ₃ Ratio 7.93 :1		Alkali Metals 0.20		Alkaline Earths 0.80	
SiO ₂ 1.99	Collective "Al ₂ O ₃ " 0.25	Na ₂ O 0.16	K ₂ O 0.05	MgO 0.38	CaO 0.39
B ₂ O ₃	Al ₂ O ₃ 0.25	Li ₂ O	CuO	SrO	BaO
TiO ₂ 0.00	NiO	Bi ₂ O ₃	SnO ₂	ZnO	FeO 0.00
Cr ₂ O ₃	ZrO ₂	P ₂ O ₅		MnO ₂	CoO 0.02



Ceramic
Materials
Workshop



Ceramic
Materials
Workshop

Cobalt Carbonate 1%


ceramicmaterialsworkshop.com



Ceramic
Materials
Workshop

Chrome Oxide 1%


ceramicmaterialsworkshop.com



Ceramic
Materials
Workshop

Copper Carbonate 3%

ceramicmaterialsworkshop.com



Ceramic
Materials
Workshop

Red Iron Oxide 6%


ceramicmaterialsworkshop.com



Ceramic
Materials
Workshop

Manganese Dioxide 3%

ceramicmaterialsworkshop.com



Oxidation



Reduction



Oxidation





Reduction



Ceramic
Materials
Workshop

Nickel Carbonate 2.5%

ceramicmaterialsworkshop.com



Ceramic
Materials
Workshop

Titanium Dioxide 6%

ceramicmaterialsworkshop.com



Ceramic
Materials
Workshop

Tin Oxide 5%

ceramicmaterialsworkshop.com



Ceramic
Materials
Workshop

Zirconium Silicate 10%

ceramicmaterialsworkshop.com